

PharmaPure®

Low Spallation Peristaltic Pump Tubing

PharmaPure® Flexibility

PharmaPure® is a premium, low spallation, biologically compatible peristaltic pump tubing developed especially for pharmaceutical, biotechnology, and laboratory applications. This tubing provides excellent pump life with ultra-low particulate spallation and very low gas permeability compared to standard silicone tubing.

Lower Spallation, Lower Risk of Contamination

The superior flex life characteristics of PharmaPure® simplify biopharmaceutical manufacturing processes by reducing production downtime due to pump tubing failures.

Its excellent wear properties allow the product to provide extremely low rates of spallation as compared to silicone and other alternate materials.

Because PharmaPure® has low permeability and lower absorption characteristics, it is ideal for protecting sensitive fluids from gas ingress and concentration changes due to fluid absorption.

Fully Characterized and Biocompatible

PharmaPure® tubing comes complete with biocompatibility, physiochemical and extractable testing which can be found in the [Validation Guide Summary](#) on the Saint-Gobain Bioprocess Solutions website.

Features / Benefits

- Ultra-low particulate spallation
- Outlasts silicone tubing in peristaltic pumps
- Provides an excellent barrier with very low permeability
- Withstands repeated autoclaving
- Custom mold and design capabilities

Typical Applications

- Cell harvest and media process systems
- Vaccine manufacturing
- Bioreactor process lines
- Aseptic filling
- Diagnostic test products
- Production filtration and fermentation

PharmaPure® Tubing Standard Sizes

Part Number	I.D. inches (mm)	O.D. inches (mm)	Wall Thickness inches (mm)	Length feet (m)	Minimum Bend Radius inches (mm)	Max. Suggested Working Pressure at		Vacuum Rating In. Hg (mm Hg)	
						73°F *psi (bar)	180°F *psi (bar)	73°F (23°C)	180°F (82°C)
AL242606	1/32 (0.8)	5/32 (4)	1/16 (1.6)	25 (7.6)	1/2 (13)	38 (2.6)	23 (1.6)	29.9 (760)	29.9 (760)
AL242002	1/16 (1.6)	1/8 (3.2)	1/32 (0.8)	25 (7.6)	1/2 (13)	20 (1.4)	13 (0.9)	29.9 (760)	29.9 (760)
AL242003	1/16 (1.6)	3/16 (4.7)	1/16 (1.6)	25 (7.6)	1/2 (13)	27 (1.9)	18 (1.2)	29.9 (760)	29.9 (760)
AL242005	3/32 (2.4)	7/32 (5.5)	1/16 (1.6)	25 (7.6)	1/2 (13)	27 (1.9)	13 (0.9)	29.9 (760)	29.9 (760)
AL242006	1/8 (3.2)	3/16 (4.8)	1/32 (0.8)	25 (7.6)	3/4 (19)	10 (0.7)	8 (0.6)	29.9 (760)	10 (254)
AL242007	1/8 (3.2)	1/4 (6.4)	1/16 (1.6)	25 (7.6)	3/4 (19)	24 (1.7)	12 (0.8)	29.9 (760)	29.9 (760)
AL242012	3/16 (4.8)	5/16 (7.9)	1/16 (1.6)	25 (7.6)	3/4 (19)	20 (1.4)	10 (0.7)	29.9 (760)	25 (635)
AL242017	1/4 (6.4)	3/8 (9.5)	1/16 (1.6)	25 (7.6)	1-1/4 (32)	15 (1.0)	7 (0.5)	29.9 (760)	15 (381)
AL242019	1/4 (6.4)	1/2 (12.7)	1/8 (3.2)	25 (7.6)	1-1/4 (32)	26 (1.8)	13 (0.9)	29.9 (760)	29.9 (760)
AL242022	5/16 (7.9)	7/16 (11.1)	1/16 (1.6)	25 (7.6)	1-1/2 (38)	13 (0.9)	7 (0.5)	29.9 (760)	10 (254)
AL242027	3/8 (9.5)	1/2 (12.7)	1/16 (1.6)	25 (7.6)	1-3/4 (44)	10 (0.7)	6 (0.4)	15 (381)	5 (127)
AL242029	3/8 (9.5)	5/8 (15.9)	1/8 (3.2)	25 (7.6)	1-1/2 (38)	19 (1.3)	10 (0.7)	29.9 (760)	29.9 (760)
AL242038	1/2 (12.7)	3/4 (19.0)	1/8 (3.2)	25 (7.6)	2-1/2 (64)	15 (1.0)	7 (0.5)	29.9 (760)	20 (508)
AL242046	5/8 (15.9)	7/8 (22.2)	1/8 (3.2)	25 (7.6)	2-3/4 (70)	12 (0.8)	6 (0.4)	25 (635)	10 (254)
AL242053	3/4 (19.0)	1 (25.4)	1/8 (3.2)	25 (7.6)	3-3/4 (95)	10 (0.7)	4 (0.3)	15 (381)	5 (127)

*Working pressures are calculated at a 1:5 ratio relative to burst pressure using ASTM D1599.

Typical Physical Properties


Property	ASTM Method	Value or Rating
Appearance	--	Opaque White
Durometer Hardness Shore A, 15 Sec	D2240-00	65
Maximum Service Temperature., °F (°C)	--	275 (135)
Low Temperature Embrittlement °F (°C)	D746-98	-89 (-67)
Water Absorption, %, 24 hours @ 73°F (23°C)	D570-98	0.04

Unless otherwise noted, all tests were conducted at room temperature (73°F). Values shown were determined on 0.075" thick extruded strip or 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.

Comparative Peristaltic Pump Tubing Life

The table below depicts hours until failure of 1/4" ID x 3/8" OD tubing. In each case, a 3-roller pump head was utilized operating at 600 RPM under room temperature (73°F). Tubing failure is measured in hours of use prior to rupture.




The performance of tubing in peristaltic pumping applications is affected by the conditions of use and equipment utilized, along with size and wall thickness of the tubing tested. The data above is presented for information only and should not be utilized for specification purposes.

Sterilization Methods

Autoclavable	Yes
Gas (Ethylene Oxide)	Yes
Gamma IR	25kGy

Spallation Rate Tubing Comparison

The following test data summarizes the spallation results of select tubing used in a peristaltic pump. In each case 1/4" ID tubing was used in a 3-roller pump head operating at 600 RPM under room temperature (73°F). Results from a minimum of 5 samples were averaged to obtain values.



PharmaPure® is a registered trademark of Saint-Gobain Life Sciences



Saint-Gobain Life Sciences

2665 Gilchrist Rd.
Akron, OH 44305
Tel: (800) 798-1554
Tel: (330) 789-9240
Fax: (330) 798-6968

Saint-Gobain Life Sciences

La Mothe-Aux-Aulnaies
89120 Charny, France
Tel: (33) 3-86-63-78-78
Fax: (33) 3-86-63-77-77

www.biopharm.saint-gobain.com

Contact us today for:
Consultations • Samples • Quotes • Orders

For registered access to Saint-Gobain Product Validation Summaries,
CLICK HERE

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Life Sciences products for all intended uses and that the materials to be used comply with all applicable medical regulatory requirements. Saint-Gobain Life Sciences assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 12 months from the date of first sale, Saint-Gobain Life Sciences warrants this product to be free of defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof.

SAINT-GOBAIN LIFE SCIENCES DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.