

ファームドBPT バイオ医薬用チューブ【参考資料】

概要

特徴： バイオ医薬、ローラーポンプ、滅菌（オートクレーブ、ガンマ線）

適合規格： USP ClassVI など（詳しくはバリデーションガイドをご参照ください。）

材質： 熱可塑性エラストマー系

詳細： 詳しくは英語版データシートをご参照ください（2ページ目以降参照）

日本での取り扱いサイズ

品番	内径		外径		片肉厚		巻長さ
	mm	(inch)	mm	(inch)	mm	(inch)	
AY242605	0.51	(0.02)	3.68	(0.145)	1.59	(0.063)	7.5
AY242606	0.79	(1/32)	3.97	(5/32)	1.59	(1/16)	7.5
AY242002	1.59	(1/16)	3.18	(1/8)	0.79	(1/32)	7.5
AY242003	1.59	(1/16)	4.76	(3/16)	1.59	(1/16)	7.5
AY242005	2.38	(3/32)	5.56	(7/32)	1.59	(1/16)	7.5
AY242006	3.18	(1/8)	4.76	(3/16)	0.79	(1/32)	7.5
AY242007	3.18	(1/8)	6.35	(1/4)	1.59	(1/16)	7.5
AY242012	4.76	(3/16)	7.94	(5/16)	1.59	(1/16)	7.5
AY242017	6.35	(1/4)	9.52	(3/8)	1.59	(1/16)	7.5
AY242019	6.35	(1/4)	12.70	(1/2)	3.18	(1/8)	7.5
AY242022	7.94	(5/16)	11.11	(7/16)	1.59	(1/16)	7.5
AY242027	9.52	(3/8)	12.70	(1/2)	1.59	(1/16)	7.5
AY242029	9.52	(3/8)	15.88	(5/8)	3.18	(1/8)	7.5
AY242038	12.7	(1/2)	19.05	(3/4)	3.18	(1/8)	7.5
AY242046	15.88	(5/8)	22.22	(7/8)	3.18	(1/8)	7.5
AY242053	19.05	(3/4)	25.40	(1)	3.18	(1/8)	7.5
AY242409	1.0		3.0		1.0		7.5
AY242816	2.0		4.0		1.0		7.5
AY242817	3.0		5.0		1.0		7.5
AY2421068	3.9		5.8		1.0		7.5
AY242818	4.0		6.0		1.0		7.5
AY242886	4.0		7.0		1.5		7.5
AY242819	4.0		8.0		2.0		7.5
AY2421320	4.9		10.0		2.6		7.5
AY2421352	6.0		10.0		2.0		7.5
AY2421382	7.0		10.0		1.5		7.5
AY2421680	8.0		12.0		2.0		7.5
AY2421353	10.0		14.0		2.0		7.5

製品の仕様、梱包、その他ここに記載されている事項についてはお客様へ事前の断りなく変更することがあります。(2019年8月26日現在)

サンゴバン株式会社 機能樹脂事業部

ライフサイエンス カスタマーサービス

〒391-0106 長野県諏訪郡原村10801-5

TEL: 0266-79-6410 FAX: 0266-70-1002

E-mail: ls-japan@saint-gobain.com

www.saint-gobain.co.jp/plastics





Saint-Gobain
Life Sciences –
Bioprocess Solutions



PharMed® BPT

Biocompatible Peristaltic Pump Tubing

Features/Benefits

- Outlasts silicone tubing in peristaltic pumps
- Withstands repeated autoclaving
- Withstands repeated CIP and SIP cleaning and sterilization
- Documented Biocompatibility
- Multiple Manufacturing sites

High Performance Peristaltic Pump Tubing

PharMed® BPT tubing has been formulated to withstand the rigors of peristaltic pumping action while providing the biocompatible fluid surface required in sensitive bioprocess applications. With its superior flex life characteristics, PharMed BPT tubing simplifies biopharmaceutical manufacturing processes by reducing production downtime due to pump tubing failure.

Simplifies Cleaning and Sterilization

PharMed® BPT tubing is ideal for use in clean-in-place and steam-in-place cleaning and sterilization systems. It is compatible with virtually all commercial cleaners and sanitizers and can be repeatedly autoclaved up to five cycles without affecting overall service life. PharMed BPT also withstands 50kGy of gamma radiation with minimal effect on physical properties.

Superior Barrier Properties

PharMed® BPT tubing is less permeable to gases and vapors than silicone tubing. It is ideal for protecting sensitive fluids in a variety of biopharmaceutical operations including media mixing, cell culture, harvest, and purification. PharMed BPT tubing has very good general chemical resistance and excellent acid, alkali and oxidation resistance. Opaque to visible and UV light, PharMed BPT tubing will help to protect light-sensitive fluids.

Fully Characterized and Biocompatible

PharMed® BPT tubing comes complete with biocompatibility, physiochemical and extractable testing which can be found in the [Validation Guide Summary](#) on the Saint-Gobain Bioprocess Solutions website.


Typical Pump Applications

- Cell harvest and media process systems
- Bioreactor process lines
- Production filtration and fermentation
- Aseptic filling
- Shear-sensitive fluid transfer
- Diagnostics and laboratory testing



Comparative Peristaltic Pump Tubing Life


The table below depicts hours until tubing rupture of 1/4" (6.4mm) ID x 3/8" (9.5mm) OD tubing. In each case, a 3-roller pump head was utilized operating at 600 rpm at room temperature 73°F (23°C).



The performance of tubing in peristaltic pumping applications is affected by the conditions of use and equipment utilized, along with size and wall thickness of the tubing tested. The data above is presented for information only and should not be utilized for specification purposes.

Permeability Coefficient Comparison

$$\text{Permeability Coefficient} = \frac{\text{amount of gas (cm}^3\text{) x tubing wall thickness (cm)}}{\text{surface area of tubing ID (cm}^2\text{) x time (sec) x pressure drop across tubing wall (cm Hg)}}$$



Typical Physical Properties of PharMed® BPT Tubing

Property	ASTM Method	Value or Rating
Appearance	—	Opaque Cream
Durometer Hardness Shore A, 15 Sec	D2240	64
Maximum Service Temperature, °F (°C)	—	275 (135)
Low Temperature Embrittlement, °F (°C)	D746	-75 (-59)
Water Absorption, % 24 hrs. @ 23°C	D570	0.30

Unless otherwise noted, all tests were conducted at room temperature (73°F). Values shown were determined on 0.075" thick extruded strip or 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

Sterilization Methods

Autoclavable	30 min at 121°C
Gas (Ethylene Oxide)	Yes
Gamma	50kGy

PharMed® BPT Standard Sizes

Part Numbers	I.D. inches (mm)	O.D. inches (mm)	Wall thickness inches (mm)	Length feet (mm)	Minimum bend radius inches (mm)	Max Working Pressure		Vacuum Rating in Hg (mm Hg)	
						at 73°F psi* (bar)	at 180°F psi* (bar)	73°F (23°C)	180°F (82°C)
AY242605	.020 (0.5)	.145 (3.7)	1/16 (1.6)	25 (7.6)	1/8 (3.2)	115 (7.9)	72 (5.0)	29.9 (760)	29.9 (760)
AY242606	1/32 (0.8)	5/32 (4.0)	1/16 (1.6)	25 (7.6)	1/8 (3.2)	78 (5.4)	49 (3.4)	29.9 (760)	29.9 (760)
AY242002	1/16 (1.6)	1/8 (3.2)	1/32 (0.79)	25 (7.6)	1/4 (6.4)	24 (1.7)	14 (1.0)	29.9 (760)	29.9 (760)
AY242003	1/16 (1.6)	3/16 (4.76)	1/16 (1.6)	25 (7.6)	1/8 (3.2)	43 (3.0)	27 (1.9)	29.9 (760)	29.9 (760)
AY242005	3/32 (2.4)	7/32 (5.6)	1/16 (1.6)	25 (7.6)	1/4 (6.4)	30 (2.1)	19 (1.3)	29.9 (760)	29.9 (760)
AY242006	1/8 (3.2)	3/16 (4.8)	1/32 (0.8)	25 (7.6)	1/2 (12.7)	13 (0.9)	8 (0.6)	25 (635)	15 (381)
AY242007	1/8 (3.2)	1/4 (6.4)	1/16 (1.6)	25 (7.6)	1/2 (12.7)	24 (1.7)	15 (1.0)	29.9 (760)	29.9 (760)
AY242012	3/16 (4.8)	5/16 (7.9)	1/16 (1.6)	25 (7.6)	5/8 (15.8)	17 (1.2)	10 (0.7)	29.9 (760)	27 (686)
AY242017	1/4 (6.4)	3/8 (9.5)	1/16 (1.6)	25 (7.6)	7/8 (22.2)	13 (0.9)	8 (0.6)	25 (635)	15 (381)
AY242019	1/4 (6.4)	1/2 (12.7)	1/8 (3.2)	25 (7.6)	3/4 (19.0)	24 (1.7)	15 (1.0)	29.9 (760)	29.9 (760)
AY242022	5/16 (7.9)	7/16 (11.1)	1/16 (1.6)	25 (7.6)	1-1/4 (31.7)	11 (0.8)	6 (0.4)	15 (381)	9 (229)
AY242027	3/8 (9.5)	1/2 (12.7)	1/16 (1.6)	25 (7.6)	1-3/8 (34.9)	9 (0.6)	5 (0.3)	10 (254)	6 (152)
AY242029	3/8 (9.5)	5/8 (15.8)	1/8 (3.2)	25 (7.6)	1-1/8 (28.5)	17 (1.2)	10 (0.7)	29.9 (760)	27 (686)
AY242038	1/2 (12.7)	3/4 (19.0)	1/8 (3.2)	25 (7.6)	1-1/8 (28.5)	10 (0.7)	8 (0.6)	25 (635)	15 (381)
AY242046	5/8 (15.9)	7/8 (22.2)	1/8 (3.2)	25 (7.6)	2-3/4 (69.8)	11 (0.8)	6 (0.4)	15 (381)	9 (229)
AY242053	3/4 (19.0)	1 (25.4)	1/8 (3.2)	25 (7.6)	3-1/2 (88.9)	9 (0.6)	5 (0.3)	10 (254)	6 (152)

*Working pressures are calculated at a 1:5 ratio relative to burst pressure using ASTM D1599.

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.



Saint-Gobain Performance Plastics

2664 Gilchrist Road
Akron, OH 44305
Tel: (330) 798-9240
Tel: (800) 798-1554
Fax: (330) 798-6968

Saint-Gobain Performance Plastics

La Mothe-Aux-Aulnaies
89120 Charny, France
Tel: (33) 3-86-63-78-78
Fax: (33) 3-86-63-77-77

www.biopharm.saint-gobain.com

Saint-Gobain Performance Plastics' manufacturing facilities have the ability to create a variety of sizes or coil lengths for your particular application needs. Contact us for a quote to meet your specific requirements.

PharMed® is a registered trademark

Contact us today for:
[Consultations](#) • [Samples](#) • [Quotes](#) • [Orders](#)

For registered access to Saint-Gobain Product Validation Summaries, [CLICK HERE](#)

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics products for all intended uses and that the materials to be used comply with all applicable medical regulatory requirements. Saint-Gobain Performance Plastics assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 12 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product to be free of defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof.

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.